

TEST REPORT:



GEOTECHNICAL
TESTING SERVICES PTY LTD

Client: Mawsons Concrete, Shepparton PO Box 1046 SHEPPARTON VIC 3630	Report N ^o 13E/0594
	Final
	Page 1 of 1

# Date Sampled: 25/2/13	# Specified Strength (MPa): 25
Date Received: 27/2/13	# Specified Slump (mm): 80

Sample Identification:	G.T.S.:	13E0594A	13E0594B	13E0594C	13E0594D	13E0594E	13E0594F
	# Client:	15304A	15304B	15304C	15304D	15304E	15304F
# Pour/Test Location:	Reference No: 15304, 25/2/13						
# Time of Sampling:	6.50am			7.47am			
# Delivery Docket Number:	1094830			1094835			
# Slump Actual (mm):	85			75			
# Type of Slump:	N			N			
# Age at Test:	7	28	28	7	28	28	
Date of Test:	4/3/13	25/3/13	25/3/13	4/3/13	25/3/13	25/3/13	
Standard Curing (days):	5	26	26	5	26	26	
Condition as Received:	AD	AD	AD	AD	AD	AD	
Average Diameter (mm):	100.0	100.0	100.0	100.2	99.8	100.0	
Height (mm):	199	199	199	199	199	200	
Type of Capping:	R	R	R	R	R	R	
Failure Type:	N	N	N	N	N	N	
Density (kg/m ³):	2340	2340	2340	2360	2340	2340	
Strength (MPa):	28.0	35.0	34.5	29.5	35.0	34.5	

denotes information provided by Client

Remarks: Additive CARBOMETUM® standard: 1.0 kg / 100 kg of cement powder

Notes:

- 1: Standard temperature zone: Temperate
- 2: Cap Type: R-Rubber, S-Sulphur
- 3: Failure Type: N-Normal, S-Shear, C-Cap Failure, O-Other (see remarks).
- 4: Density calculated on uncapped specimens unless otherwise stated.
- 5: Testing in accordance with AS 1012.9 & 12.1 unless otherwise stated.
- 6: Condition of specimen: A-Good, B-Minor Damage, F-Major Damage, D-Damp, E-Dry, G-Non Standard, R-Rejected.
- 7: # This Laboratory shall not be responsible for the correctness or the accuracy of information shown on this report which has been provided by the client. This information includes Project, Sample Location, Identification, Type and Date Sampled.

Approved Signatory:

N.J. Fieldew

Date: 25 March, 2013

Echuca: Corporate Site #16874

Shed 3, 140 Ogilvie Ave, Echuca, 3564

PO Box 2131, Echuca, 3564 Ph (03) 5480 0601, Fax (03) 5480 6520

The results of the tests included in this document are traceable to Australian/National Standards. Accredited for compliance with ISO/IEC 17025.

This document shall not be reproduced, except in full.



Laboratory accreditation number 842.

ACN: 106 940 194
ABN: 41 106 940 194

Offices: Adelaide, Bendigo, Broken Hill, Echuca, Mildura and Noosaville Web: www.geotest.com.au Email: info@geotest.com.au

- Geotechnical Investigations • Contract Drilling • Land Capability Assessments • Contamination Assessments • Compaction Control Testing • On-site Wastewater Management
- Site Classifications - Residential and Industrial • Soil, Concrete and Aggregate Testing Laboratories • Site Laboratory • Construction Material Testing Services